

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
㈜ 에스엠프로토	SAMPLE(무)	260812-01	2026.08.12
MATERIAL(재질)	SPEC		수량
C1100	Ni: 1.0~ μm Sn: 3.0~ μm		36 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0 μm ~				
12	PLATING THICKNESS (Sn)	3.0 μm ~ μm				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

(주) 에스엠프로토 Ni: 1.0~ μm Sn: 3.0~ μm

수량 : EA



품명 SAMPLE() LOT NO: 260812-01 일자: 2026.08.12.

No	μm Sn	μm Ni	Sn tolerance
1	3.385	1.235	3.204 4.001 4.798
2	3.204	1.291	
3	4.599	1.140	
4	4.420	1.184	
5	4.397	1.236	
Mean	4.001	1.217	
S.Dev	0.584	0.051	

FUNC: MEASURE
DATE: 2026-08-12
COL : 1.000 mm

Sn
Ni
Cu

SEC : 15 Sec



도금원소 : Sn/Ni//Cu

측정값 개수	5	5
최대값	4.599	1.291
최소값	3.204	1.140
범위	1.395	0.151
평균값	4.001	1.217
표준편차	0.584	0.051
변동계수	14.594	4.218

발행처 : 우리하이피

