

# Quality Assurance Report (신형)

| CUSTOMER(고객명) | DESCRIPTION(품명)      | PLATING DATE(도금일자) | ISSUED DATE(발행일자) |
|---------------|----------------------|--------------------|-------------------|
| 나담전자          | 극주 BUSBAR (M)        | 2026.09.08         | 2026.09.08        |
| MATERIAL(재질)  | SPEC                 |                    | 수량                |
| C1100         | Nip: 3.0~4.0 $\mu$ m |                    | 67 EA             |

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |


## II.DIMENSION INSPECTION

| NO | INSPECTION ITEMS        | SPECIFICATION        | MIN | MAX | AVERAGE | RESULT |
|----|-------------------------|----------------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Nip) | Nip: 3.0~4.0 $\mu$ m |     |     |         |        |
| 12 |                         |                      |     |     |         |        |
| 13 |                         |                      |     |     |         |        |
| 14 |                         |                      |     |     |         |        |

도금두께 성적서 참조

## III.FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY                                                                            | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|  |        | 우데스         |  |  |

나담전자

NiP : 3.0~4.0 $\mu$ m

수량: EA

품명: 극주 BUSBAR (M)

LOT NO: 260908-01


일자: 2025.09.08.

| No    | $\mu$ m<br>NiP | NiP tolerance |       |       |
|-------|----------------|---------------|-------|-------|
|       |                | 3.265         | 3.318 | 3.371 |
| 1     | 3.316          |               |       |       |
| 2     | 3.265          |               |       |       |
| 3     | 3.336          |               |       |       |
| 4     | 3.352          |               |       |       |
| 5     | 3.320          |               |       |       |
| Mean  | 3.318          |               |       |       |
| S.Dev | 0.029          |               |       |       |

FUNC: MEASURE  
DATE: 2026-09-08  
COL : 0.400 mm

NiP  
Cu

SEC : 15 Sec



도금원소 : NiP//Cu

측정값 개수 5

최대값 3.352

최소값 3.265

범위 0.087

평균값 3.318

표준편차 0.029

변동계수 0.884

발행처 : 우리하이피

