

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 04	260817_01	2026.08.17
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		1,300 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

고객명:나담테크

Ni: 5.0 μ m~

품명: JF 2 BUSBAR 04 LOT NO: 260817-01


일자: 2026.08.17

FUNC: MEASURE
DATE: 2026-08-17
COL : 1.000 mm

No	μ m Ni	Ni tolerance	
		5.853	6.557 7.261
1	6.104		
2	6.228		
3	6.457		
4	6.735		
5	7.261		
Mean	6.557		
S.Dev	0.412		

Ni
Cu

SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 7.261
최소값 6.104
범위 1.157
평균값 6.557
표준편차 0.412
변동계수 6.291

우리하이피

