

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	SENSING TAP B	2026.08.18-01	2026-08-18
MATERIAL(재질)	SPEC		수량
C1100	Sn: 1.0~3.0 μ m		50 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Sn)	1.0~3.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

나담테크

Sn: 1.0~3.0 μ m

품명 : SENSING TAP B

LOT NO: 260818-01


일자: 2026.08.18

No	μ m Sn	Sn tolerance
1	1.493	1.347 1.437 1.527
2	1.347	
3	1.362	
4	1.496	
5	1.486	
Mean	1.437	
S.Dev	0.067	

FUNC: MEASURE
DATE: 2026-08-18
COL : 1.000 mm

Sn
Ni
Cu

SEC : 15 Sec



도금원소 : Sn/Ni//Cu

측정값 개수 5

최대값 1.496

최소값 1.347

범위 0.149

평균값 1.437

표준편차 0.067

변동계수 4.694

우리하이피

