

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 04	260820_01	2026.08.20
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0μm~		1,020 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0μm~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
합격 2026.08.20 (주) Q.C		우데스		

고객명:나담테크

Ni: 5.0 μ m~

품명: JF 2 BUSBAR 04 LOT NO: 260820-01


일자: 2026.08.20

No	μ m Ni	Ni tolerance	
		5.881	6.168 6.456
1	6.136		
2	5.975		
3	6.456		
4	6.027		
5	6.248		
Mean	6.168		
S.Dev	0.172		

FUNC: MEASURE
DATE: 2026-08-20
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 6.456

최소값 5.975

범위 0.481

평균값 6.168

표준편차 0.172

변동계수 2.784

우리하이피

