

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 02	260827_01	2026.08.27
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		7,268 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

고객명:나담테크

Ni: 5.0 μ m~

품명: JF 2 BUSBAR 02 LOT NO: 260827-01


일자: 2026.08.27

No	μ m Ni	Ni tolerance	
		5.839	6.454 7.069
1	5.839		
2	6.258		
3	6.754		
4	6.818		
5	6.601		
Mean	6.454		
S.Dev	0.364		

FUNC: MEASURE
DATE: 2026-08-27
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 6.818


최소값 5.839

범위 0.979

평균값 6.454

표준편차 0.364

변동계수 5.633



우리하이피