

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 02	260831_01	2026.08.31
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		2,527 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

나담테크 Ni: 5.0 μ m~ 수량 : EA

품명 : JF 2 BUSBAR 02 LOT NO : 260831-01


일자 : 2026.08.31.

No	μ m Ni	Ni tolerance
1	6.457	6.432 6.622 6.812
2	6.735	
3	6.690	
4	6.432	
5	6.796	
Mean	6.622	
S.Dev	0.149	

FUNC: MEASURE
DATE: 2026-08-31
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 6.796
최소값 6.432
범위 0.364
평균값 6.622
표준편차 0.149
변동계수 2.250

발행처 : 우리하이피

