

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 04	260831_01	2026.08.31
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		1,475 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
합격 2026.08.31 (주) Q.C		우데스		

나담테크 Ni: 5.0 μ m~ 수량 : EA

품명 : JF 2 BUSBAR 04 LOT NO : 260831-01


일자 : 2026.08.31.

No	μ m Ni	Ni tolerance
1	5.833	5.833 6.152 6.471
2	6.351	
3	6.011	
4	6.104	
5	6.460	
Mean	6.152	
S.Dev	0.227	

FUNC: MEASURE
DATE: 2026-08-31
COL : 1.000 mm

Ni
Cu

SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 6.460
최소값 5.833
범위 0.627
평균값 6.152
표준편차 0.227
변동계수 3.695

발행처 : 우리하이피

