

# Quality Assurance Report

|               |                                             |                    |                   |
|---------------|---------------------------------------------|--------------------|-------------------|
| CUSTOMER(고객명) | DESCRIPTION(품명)                             | PLATING DATE(도금일자) | ISSUED DATE(발행일자) |
| 나담테크          | COUNTI SUPPORT                              | 250901-01          | 2025.09.01        |
| MATERIAL(재질)  | SPEC                                        |                    | 수량                |
| Fe            | Ni : 1.0~3.0 $\mu$ m / Ag : 3.0~5.0 $\mu$ m |                    | 208 EA            |

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |


## II.DIMENSION INSPECTION

| NO | INSPECTION ITEMS       | SPECIFICATION   | MIN | MAX | AVERAGE | RESULT |
|----|------------------------|-----------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Ni) | 1.0~3.0 $\mu$ m |     |     |         |        |
| 12 | PLATING THICKNESS (Ag) | 3.0~5.0         |     |     |         |        |
| 13 |                        |                 |     |     |         |        |
| 14 |                        |                 |     |     |         |        |

도금두께 성적서 참조

## III.FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY                                                                            | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|  |        | 우데스         |  |  |

나담테크      Ni : 1.0~3.0 $\mu$ m / Ag : 3.0~5.0  $\mu$ m      수량 :      EA



품명 : COUNTI SUPPORT      LOT NO : 260901-01      일자 : 2026.09.01.

| No    | $\mu$ m<br>Ag | $\mu$ m<br>Ni | Ag tolerance |       |       |
|-------|---------------|---------------|--------------|-------|-------|
|       |               |               | 4.430        | 4.605 | 4.780 |
| 1     | 4.549         | 2.778         |              |       |       |
| 2     | 4.461         | 2.850         |              |       |       |
| 3     | 4.524         | 2.648         |              |       |       |
| 4     | 4.711         | 2.575         |              |       |       |
| 5     | 4.780         | 2.768         |              |       |       |
| Mean  | 4.605         | 2.724         |              |       |       |
| S.Dev | 0.120         | 0.099         |              |       |       |

FUNC: MEASURE  
DATE: 2026-09-01  
COL : 0.200 mm

Ag  
Ni  
Fe

SEC : 15 Sec



도금원소 : Ag/Ni//Fe

|        |       |       |
|--------|-------|-------|
| 측정값 개수 | 5     | 5     |
| 최대값    | 4.780 | 2.850 |
| 최소값    | 4.461 | 2.575 |
| 범위     | 0.319 | 0.275 |
| 평균값    | 4.605 | 2.724 |
| 표준편차   | 0.120 | 0.099 |
| 변동계수   | 2.611 | 3.623 |

발행처 : 우리하이피

