

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 03	260903_01	2026.09.07
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		1,101 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling	PASS	OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		나우인		


세명: 나담테크

Ni: 5.0 μ m ~

품명: JF 2 BUSBAR 03


LOT NO : 20260907-01

일자: 2026.09.07.

No	μ m Ni	Ni tolerance		
		10.606	10.719	10.832
1	10.606			
2	10.759			
3	10.720			
4	10.813			
5	10.697			
Mean	10.719			
S.Dev	0.069			

FUNC: MEASURE
DATE: 2026-09-07
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 10.813

최소값 10.606

범위 0.207

평균값 10.719

표준편차 0.069

변동계수 0.642

발행처 : 우리하이피

