

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	대창 BUSBAR 02	260909-01	2026.09.09.
MATERIAL(재질)	SPEC		수량
C1100	Ni : 3.0~7.0~ μ m		915 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	3.0~7.0~ μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

나담테크

Ni: 3.0~7.0 μ m

품명:SS BATT BUSBAR-2

LOT NO: 260909-1


일자: 2026.09.09.

No	μ m Ni	Ni tolerance
1	5.302	5.262 5.312 5.362
2	5.292	
3	5.310	
4	5.294	
5	5.362	
Mean	5.312	
S.Dev	0.026	

FUNC: MEASURE
DATE: 2026-09-09
COL : 1.000 mm

Ni
Cu

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 5.362

최소값 5.292

범위 0.070

평균값 5.312

표준편차 0.026

변동계수 0.486

우리하이피

