

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 03	260909-1~3	2026.09.11
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		3,564 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling	PASS	OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		나우인		

고객명:나담테크

Ni: 5.0 μ m~


품명: JF 2 BUSBAR 03 LOT NO: 260909-01^ㄴ

일자: 2026.09.09

No	μ m Ni	Ni tolerance	
		6.013	6.508 7.004
1	6.320		
2	6.348		
3	6.174		
4	6.696		
5	7.004		
Mean	6.508		
S.Dev	0.301		

FUNC: MEASURE
DATE: 2026-09-09
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 7.004
최소값 6.174
범위 0.830
평균값 6.508
표준편차 0.301
변동계수 4.629

우리하이피

