

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
나담테크	JF 2 BUSBAR 04	260910-1	2026.09.11
MATERIAL(재질)	SPEC		수량
C1100	Ni: 5.0 μ m~		4,081 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	5.0 μ m~				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling	PASS	OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		나우인		

고객명:나담테크

Ni: 5.0 μ m~

품명: JF 2 BUSBAR 04 LOT NO: 260910-01


일자: 2026.09.10.

No	μ m Ni	Ni tolerance	
		8.902	9.034 9.166
1	8.902		
2	9.094		
3	9.062		
4	8.946		
5	9.166		
Mean	9.034		
S.Dev	0.097		

FUNC: MEASURE
DATE: 2026-09-10
COL : 1.000 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 9.166


최소값 8.902

범위 0.264

평균값 9.034

표준편차 0.097

변동계수 1.073



우리하이피