

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
(주)벡스플러스	BUSBAR POSITIVE	260812-01	2026.08.12
MATERIAL(재질)	SPEC		수량
Al	Ni: 1.0~5.0 μ m Sn: 4.0~10.0 μ m		78 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~5.0 μ m				
12	PLATING THICKNESS (Sn)	4.0~10.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

(주)백스플러스 Ni: 1.0~5.0 μ m Sn: 4.0~10.0 μ m



품명: BUSBAR POSITIVE LOT NO: 260812-01 일자: 2026.08.12.

No	μ m Sn	μ m Ni	Sn tolerance 6.907 7.605 8.303
1	7.018	1.956	
2	8.210	2.337	
3	7.452	1.875	
4	7.043	2.047	
5	8.303	2.357	
Mean	7.605	2.114	
S.Dev	0.554	0.198	

FUNC: MEASURE
DATE: 2026-08-12
COL : 0.400 mm

Sn
Ni
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	5	5
최대값	8.303	2.357
최소값	7.018	1.875
범위	1.285	0.482
평균값	7.605	2.114
표준편차	0.554	0.198
변동계수	7.290	9.348

발행처 : 우리하이피

