

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
(주)벅스플러스	BUSBAR NEGATIVE	260813-01	2026.08.13
MATERIAL(재질)	SPEC		수량
Al	Ni: 1.0~5.0 μ m Sn: 4.0~10.0 μ m		660 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~5.0 μ m				
12	PLATING THICKNESS (Sn)	4.0~10.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

(주)넥스플러스 Ni: 1.0~5.0 μ m Sn: 4.0~10.0 μ m

품명: BUSBAR NEGATIVE LOT NO: 260813-01



일자: 2026.08.13.

No	μ m Sn	μ m Ni	Sn tolerance		
			4.633	5.705	6.777
1	6.030	3.257			
2	4.633	2.477			
3	5.492	2.611			
4	6.163	3.195			
5	6.208	2.908			
Mean	5.705	2.890			
S.Dev	0.594	0.309			

FUNC: MEASURE
DATE: 2026-08-13
COL : 0.400 mm

Sn
Ni
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	5	5
최대값	6.208	3.257
최소값	4.633	2.477
범위	1.575	0.780
평균값	5.705	2.890
표준편차	0.594	0.309
변동계수	10.408	10.683

발행처 : 우리하이피

