

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
성경정밀주식회사	PIPE	2026.08.10-01~10	2026-08-10
MATERIAL(재질)	SPEC		수량
(황동)	Ni : 3.0~5.0 μ m		20,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	3.0~5.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

성경정밀(주)

Ni : 3.0~5.0 μ m

품명: PIPE

LOT NO: 260810-01


일자: 2026.08.10

No	μ m Ni	Ni tolerance	
		3.520	3.925 4.330
1	4.128		
2	3.520		
3	3.627		
4	4.092		
5	4.259		
Mean	3.925		
S.Dev	0.294		

FUNC: MEASURE
DATE: 2026-08-10
COL : 1.000 mm

Sn
Ni
Brass

SEC : 15 Sec



도금원소 : Sn/Ni//Brass

측정값 개수 5

최대값 4.259

최소값 3.520

범위 0.739

평균값 3.925

표준편차 0.294

변동계수 7.501

발행처 : 우리하이피

