

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
성경정밀㈜	YOKE LOWER	2026.09.12	2026-09-12
MATERIAL(재질)	SPEC		수량
Fe	Cu: 2.0~3.0 μ m Ni: 3.0~8.0 μ m		4,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(오염)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Cu)	2.0~3.0 μ m				
12	PLATING THICKNESS (Ni)	3.0~8.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

성경정밀(주) Cu: 2.0~3.0 μ m Ni: 3.0~8.0 μ m

품명: YOKE LOWER

LOT NO: 260912-01



일자: 2026.09.12

FUNC: MEASURE
DATE: 2026-09-12
COL : 1.000 mm

No	μ m Cu	μ m Ni	Cu tolerance
1	2.313	5.343	2.275 2.342 2.409
2	2.282	5.481	
3	2.392	4.626	
4	2.409	4.767	
5	2.315	4.953	
Mean	2.342	5.034	
S.Dev	0.049	0.329	

Cu
Ni
Fe

SEC : 15 Sec



도금원소 : Cu/Ni//Fe

측정값 개수	5	5
최대값	2.409	5.481
최소값	2.282	4.626
범위	0.127	0.855
평균값	2.342	5.034
표준편차	0.049	0.329
변동계수	2.105	6.526

발행처 : 우리하이피

