

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
성경정밀㈜	YOKE UPPER	2026.09.12	2026-09-12
MATERIAL(재질)	SPEC		수량
Fe	Cu: 2.0~3.0 μ m Ni: 3.0~8.0 μ m		4,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Cu)	2.0~3.0 μ m				
12	PLATING THICKNESS (Ni)	3.0~8.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채	/	

성경정밀(주) Cu: 2.0~3.0 μ m Ni: 3.0~8.0 μ m

품명: YOKE UPPER

LOT NO: 260912-01



일자: 2026.09.12

No	μ m Cu	μ m Ni	Cu tolerance		
			2.077	2.174	2.271
1	2.222	4.116			
2	2.163	4.310			
3	2.103	4.304			
4	2.271	3.748			
5	2.110	3.645			
Mean	2.174	4.025			
S.Dev	0.065	0.279			

FUNC: MEASURE
DATE: 2026-09-12
COL : 1.000 mm

Cu
Ni
Fe

SEC : 15 Sec



도금원소 : Cu/Ni//Fe

측정값 개수	5	5
최대값	2.271	4.310
최소값	2.103	3.645
범위	0.168	0.665
평균값	2.174	4.025
표준편차	0.065	0.279
변동계수	2.979	6.926

발행처 : 우리하이피

