

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코백	DUMMY-D938468	2026.08.21	2026.08.21
MATERIAL(재질)	SPEC	수량	
Al	Nip : 2.0~4.0 μ m	17,700 EA	

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

에스코넥

NiP : 2.0~4.0 μ m

수량 :

EA

품명 : DUMMY D-938468 LOT NO : 260821-01


일자 : 2026.08.21.

No	μ m NiP	NiP tolerance		
		2.604	2.874	3.144
1	2.931			
2	2.801			
3	2.604			
4	3.121			
5	2.913			
Mean	2.874			
S.Dev	0.170			

FUNC: MEASURE
DATE: 2026-08-21
COL : 1.000 mm

NiP
Al

SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 3.121

최소값 2.604

범위 0.517

평균값 2.874

표준편차 0.170

변동계수 5.905

발행처 : 우리하이피

