

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코백	DUMMY-D747428	2026.08.26	2026.08.26
MATERIAL(재질)	SPEC		수량
Al	Nip : 2.0~4.0 μ m		12,800 EA

I. VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			



II. DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III. FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

에스코백 Nip : 2.0~4.0 μ m

수량 : EA


품명 : DUMMY D-747428 LOT NO : 260826-01

일자 : 2026.08.26.

No	μ m NiP	NiP tolerance		
		3.017	3.278	3.538
1	3.367			
2	3.345			
3	3.398			
4	3.261			
5	3.017			
Mean	3.278			
S.Dev	0.138			

FUNC: MEASURE
DATE: 2026-08-26
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$
SEC : 15 Sec



도금원소 : NiP//Al
측정값 개수 5
최대값 3.398
최소값 3.017
범위 0.381
평균값 3.278
표준편차 0.138
변동계수 4.210

발행처 : 우리하이피

