

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코넥	DUMMY-D938468	2026.08.31	2026.08.31
MATERIAL(재질)	SPEC		수량
Al	Nip : 2.0~4.0 μ m		17,930 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

에스코백

Nip : 2.0~4.0 μ m

수량 :

EA


품명 : DUMMY D-938468 LOT NO : 260831-01

일자 : 2026.08.31.

No	μ m NiP	NiP tolerance
1	2.753	2.753 2.900 3.046
2	2.962	
3	2.881	
4	2.885	
5	3.017	
Mean	2.900	
S.Dev	0.089	

FUNC: MEASURE
DATE: 2026-08-31
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$
SEC : 15 Sec



도금원소 : NiP//Al
측정값 개수 5
최대값 3.017
최소값 2.753
범위 0.264
평균값 2.900
표준편차 0.089
변동계수 3.074

발행처 : 우리하이피

