

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코백	DUMMY-D938468	2026.09.10	2026.09.10
MATERIAL(재질)	SPEC		수량
Al	Nip : 2.0~4.0 μ m		15,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			



II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

에스코넥

NiP : 2.0~4.0 μ m

수량 : EA

품명 : DUMMY D-938468 LOT NO : 260910-01


일자 : 2026.09.10.

No	μ m NiP	NiP tolerance
1	3.019	2.529 2.774 3.019
2	2.625	
3	2.739	
4	2.628	
5	2.860	
Mean	2.774	
S.Dev	0.150	

FUNC: MEASURE
DATE: 2026-09-10
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$

SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 3.019

최소값 2.625

범위 0.394

평균값 2.774

표준편차 0.150

변동계수 5.399

발행처 : 우리하이피

