

# Quality Assurance Report

| CUSTOMER(고객명) | DESCRIPTION(품명)                         | PLATING DATE(도금일자) | ISSUED DATE(발행일자) |
|---------------|-----------------------------------------|--------------------|-------------------|
| 한중엔시에스        | BUSBAR MTM(SAMPLE)                      | 260812-01          | 2026.08.12        |
| MATERIAL(재질)  | SPEC                                    |                    | 수량                |
| Al            | Ni: 1.0~5.0 $\mu$ m Sn: 5.0~9.0 $\mu$ m |                    | 2 EA              |

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |

## II.DIMENSION INSPECTION

| NO | INSPECTION ITEMS       | SPECIFICATION   | MIN | MAX | AVERAGE | RESULT |
|----|------------------------|-----------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Ni) | 1.0~5.0 $\mu$ m |     |     |         |        |
| 12 | PLATING THICKNESS (Sn) | 5.0~9.0 $\mu$ m |     |     |         |        |
| 13 |                        |                 |     |     |         |        |
| 14 |                        |                 |     |     |         |        |

도금두께 성적서 참조

## III.FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|------------|---------------------------------------------------------------------------------------|
|  |        | 우데스         |            |  |

한중엔시에스

Ni: 1.0~5.0 $\mu$ m Sn: 5.0~10.0 $\mu$ m

품명: BUSBAR MTM(SAMPLE) OT NO: 260812-01



일자: 2026.08.12.

| No    | $\mu$ m<br>Sn | $\mu$ m<br>Ni | Sn tolerance      |
|-------|---------------|---------------|-------------------|
| 1     | 8.176         | 4.757         | 7.465 7.821 8.176 |
| 2     | 7.643         | 3.342         |                   |
| 3     | 8.021         | 3.733         |                   |
| 4     | 7.683         | 3.582         |                   |
| 5     | 7.580         | 3.740         |                   |
| Mean  | 7.821         | 3.831         |                   |
| S.Dev | 0.234         | 0.485         |                   |

FUNC: MEASURE  
DATE: 2026-08-12  
COL : 0.400 mm

Sn  
Ni  
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

|        |       |        |
|--------|-------|--------|
| 측정값 개수 | 5     | 5      |
| 최대값    | 8.176 | 4.757  |
| 최소값    | 7.580 | 3.342  |
| 범위     | 0.596 | 1.415  |
| 평균값    | 7.821 | 3.831  |
| 표준편차   | 0.234 | 0.485  |
| 변동계수   | 2.998 | 12.662 |

발행처 : 우리하이피

