

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE	ISSUED DATE(발행일자)
호연이엔지	HOLD DOWN PIN	260823-01-10	2026.08.23
MATERIAL(재질)	SPEC		수량
SUS	Ni : 1.0~3.0 μ m		510,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

연이엔

Ni : 1.0~3.0 μ m

수량:

EA

품명: HOLD DOWN PIN

LOT NO : 260823-01


일자: 2023.08.23

FUNC: MEASURE
DATE: 2026-08-23
COL : 0.400 mm

No	μ m Ni	Ni tolerance
1	1.777	1.524 1.872 2.221
2	1.945	
3	1.524	
4	1.991	
5	2.125	
Mean	1.872	
S.Dev	0.207	

Au
Ni
SS

SEC : 15 Sec



도금원소 : Au/Ni//SS

측정값 개수 5
최대값 2.125
최소값 1.524
범위 0.601
평균값 1.872
표준편차 0.207
변동계수 11.039

발행처 : 우리하이피

