

# Quality Assurance Report

|               |                      |              |                   |
|---------------|----------------------|--------------|-------------------|
| CUSTOMER(고객명) | DESCRIPTION(품명)      | PLATING DATE | ISSUED DATE(발행일자) |
| 호연이엔지         | HOLD DOWN PIN        | 260901-01-40 | 2026.09.01        |
| MATERIAL(재질)  | SPEC                 |              | 수량                |
| SUS           | Ni : 1.0~3.0 $\mu$ m |              | 400,000 EA        |

## I.VISUAL INSPECTION

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |


## II.DIMENSION INSPECTION

| NO | INSPECTION ITEMS       | SPECIFICATION   | MIN | MAX | AVERAGE | RESULT |
|----|------------------------|-----------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Ni) | 1.0~3.0 $\mu$ m |     |     |         |        |
| 12 |                        |                 |     |     |         |        |
| 13 |                        |                 |     |     |         |        |
| 14 |                        |                 |     |     |         |        |

도금두께 성적서 참조

## III.FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|------------|---------------------------------------------------------------------------------------|
|  |        | 우데스         |            |  |

주)호연이엔

Ni : 1.0~3.0 $\mu$ m

수량:

EA

품명: HOLD DOWN PIN

LOT NO : 260901-01


일자: 2026.09.01

| No    | $\mu$ m<br>Ni | Ni tolerance      |
|-------|---------------|-------------------|
| 1     | 1.725         | 1.725 1.970 2.216 |
| 2     | 2.165         |                   |
| 3     | 1.976         |                   |
| 4     | 1.896         |                   |
| 5     | 2.090         |                   |
| Mean  | 1.970         |                   |
| S.Dev | 0.154         |                   |

FUNC: MEASURE  
DATE: 2026-09-01  
COL : 0.400 mm

Au  
Ni  
SS

SEC : 15 Sec



도금원소 : Au/Ni//SS

측정값 개수 5

최대값 2.165


최소값 1.725

범위 0.440

평균값 1.970

표준편차 0.154

변동계수 7.795



발행처 : 우리하이피