

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE	ISSUED DATE(발행일자)
호연이엔지	HOLD DOWN PIN	260902-01-12	2026.09.02
MATERIAL(재질)	SPEC		수량
SUS	Ni : 1.0~3.0 μ m		123,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(일룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

호연이엔지

Ni : 1.0~3.0 μ m

수량:

EA

품명: HOLD DOWN PIN

LOT NO : 260902-01


일자: 2026.09.02

No	μ m Ni	Ni tolerance
1	2.021	1.762 1.925 2.089
2	1.864	
3	1.762	
4	1.957	
5	2.023	
Mean	1.925	
S.Dev	0.100	

FUNC: MEASURE
DATE: 2026-09-02
COL : 0.400 mm

Au
Ni
SS

SEC : 15 Sec



도금원소 : Au/Ni//SS

측정값 개수 5

최대값 2.023

최소값 1.762

범위 0.261

평균값 1.925

표준편차 0.100

변동계수 5.201

발행처 : 우리하이피

