

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE	ISSUED DATE(발행일자)
호연이엔지	HOLD DOWN PIN	260910-01~56	2026.09.10
MATERIAL(재질)	SPEC		수량
SUS	Ni : 1.0~3.0 μ m		560,000 EA

I. VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II. DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III. FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

호연이엔지

Ni : 1.0~3.0 μ m

품명: HOLD DOWN PIN

LOT NO : 260910-01


일자: 2026.09.10.

No	μ m Ni	Ni tolerance	
		1.723	1.854 1.986
1	1.723		
2	1.769		
3	1.969		
4	1.938		
5	1.873		
Mean	1.854		
S.Dev	0.095		

FUNC: MEASURE
DATE: 2026-09-10
COL : 0.400 mm

Au
Ni
SS

SEC : 15 Sec



도금원소 : Au/Ni//SS

측정값 개수 5

최대값 1.969

최소값 1.723

범위 0.246

평균값 1.854

표준편차 0.095

변동계수 5.117

발행처 : 우리하이피

