



Quality Assurance Report

8P6T930960 / 8P6T931040

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
풍산	0.15*90	20260907 -01 2	2026-09-07
규격(재질)		LOT SIZE(수량)	
0.15*107 Cu	Ni 1.0~2.0μm	217 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSP	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 박리)	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금 덩어리)	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	OK
5	BENT(변형)	0/1	OK	10	PLATING BLANK	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=100mm/EA, 2EA/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		판정
		규격	하한(-)	상한(+)		1차	2차	
1	전폭	175.0	-0.1		Reel/Lot	89.974		OK
2								
3								
4								
5								
6								
7								
8								
9								
10								

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금물 이나 벗겨짐이 없을것.		K
제품 도면				
	고 객	작성	승인	종합 판정

업체명 : 풍산

품명 : 0.15x90 초물 LOT NO : 260907-01 DATE : 26.09.07.

No	μm Ni	Ni tolerance	
		1.651	1.688 1.725
1	1.685		
2	1.683		
3	1.715		
4	1.706		
5	1.651		
Mean	1.688		
S.Dev	0.025		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

표준편차 0.025
변동계수 1.468

우리하이피



업체명 : 풍산


품명 : 0.15x90 종물 LOT NO : 260907-01 DATE : 26.09.07.

No	μm Ni	Ni tolerance
1	1.712	1.654 1.685 1.715
2	1.714	
3	1.667	
4	1.676	
5	1.654	
Mean	1.685	
S.Dev	0.027	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.714
최소값 1.654
범위 0.060
평균값 1.685
표준편차 0.027
변동계수 1.608

우리하이피

