

업체명 : 넥스플러스 Sn : 4 ~ 10 μ m / Ni : 1 ~ 5 μ m



품명: BUSBAR NEG NEW RACK 앞 LOT NO: 260806-01

일자: 2026.08.06

No	μ m Sn	μ m Ni	Sn tolerance
1	8.902	4.680	5.087 7.322 9.558
2	8.335	4.426	
3	7.192	3.449	
4	7.945	4.293	
5	7.480	3.367	
6	6.984	2.935	
7	6.008	4.095	
8	7.065	3.599	
9	7.309	4.080	
10	7.568	4.533	
11	5.087	3.351	
12	7.083	3.358	
13	6.712	3.204	
14	7.089	3.747	
15	8.474	3.978	
16	7.924	4.479	
Mean	7.322	3.848	
S.Dev	0.904	0.526	

FUNC: MEASURE
DATE: 2026-08-07
COL : 0.400 mm


Sn
Ni
Al
SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	16	16
최대값	8.902	4.680
최소값	5.087	2.935
범위	3.815	1.745
평균값	7.322	3.848
표준편차	0.904	0.526
변동계수	12.352	13.660

우리하이피



업체명 : 넥스플러스 Sn : 4 ~ 10 μ m / Ni : 1 ~ 5 μ m

품명: BUSBAR NEG NEW RACK 뒤 LOT NO: 260806-01



일자: 2026.08.06

No	μ m Sn	μ m Ni	Sn tolerance
			6.339 8.236 10.133
1	9.229	4.506	
2	9.594	4.478	
3	8.411	3.496	
4	9.015	4.009	
5	7.809	4.962	
6	8.553	3.017	
7	8.097	4.648	
8	8.593	3.835	
9	6.339	4.029	
10	8.137	3.975	
11	8.231	4.085	
12	7.814	3.935	
13	8.078	3.741	
14	7.494	3.819	
15	8.395	3.740	
16	7.984	4.689	
Mean	8.236	4.060	
S.Dev	0.722	0.479	

FUNC: MEASURE
DATE: 2026-08-07
COL : 0.400 mm

Sn
Ni
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	16	16
최대값	9.594	4.962
최소값	6.339	3.017
범위	3.255	1.945
평균값	8.236	4.060
표준편차	0.722	0.479
변동계수	8.771	11.803

우리하이피

