

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE	ISSUED DATE(발행일자)
한중NCS.	BUSBAR MTM	2026.08.03	2026.08.03
MATERIAL(재질)	SPEC		수량
AL	Ni : 1~5 μ m / Sn : 4 ~ 10 μ m		600 EA

I. VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II. DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	4.0~10.0 μ m				
12	PLATING THICKNESS (Sn)	1.0~5.0 μ m				
13						
14						

도금두께 성적서 참조

III. FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	CROSS CUT 기준 만족할 것.	시료 참조	OK
16		밴딩 시험 후 기준 만족할 것.	시료 참조	OK

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		나우인		

고객명:한중NCS.

Ni: 1-5um / Sn 4-10um



품명: BUSBAR MTM LOT NO: 260803-01

일자: 2026.08.03

No	μm Sn	μm Ni	Sn tolerance
1	8.620	3.230	5.467 7.343 9.218
2	8.697	3.297	
3	7.609	2.389	
4	6.856	2.206	
5	5.620	1.789	
6	6.664	2.192	
7	8.109	3.043	
8	8.173	3.226	
9	8.741	3.676	
10	9.218	3.808	
11	6.271	2.072	
12	6.723	2.000	
13	6.314	1.726	
14	6.449	2.165	
15	6.075	1.872	
Mean	7.343	2.579	
S.Dev	1.124	0.694	

FUNC: MEASURE
DATE: 2026-08-03
COL : 0.400 mm

Sn
Ni
Al
SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	15	15
최대값	9.218	3.808
최소값	5.620	1.726
범위	3.598	2.082
평균값	7.343	2.579
표준편차	1.124	0.694
변동계수	15.306	26.911

우리하이피

