



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
동일메탈	0.1*171	20260911 -01	2026-09-11
규격(재질)		LOT SIZE(수량)	
0.1*171 C7701-1/2	Ni 1.0~3.0μm	150.4 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK






II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		고객		판정
		규격	하한(-)	상한(+)		1차	2차	1차	2차	
1	전폭	171.0	-0.1		Reel/Lot	171.020				OK
2										
3										
4										
5										
6										
7										
8										
9										
10										

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~3.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, 3%)					RESULT
NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE		
1					OK
제품도면			작성	승인	종합판정
					

9-11
(주)

동일메탈

: 0.1X171

초물

LOT NO : 260911-01 DATE : 26.09.11.

No	μm Ni	Ni tolerance
1	1.487	1.428 1.476 1.523
2	1.499	
3	1.428	
4	1.486	
5	1.478	
Mean	1.476	
S.Dev	0.028	


FUNC: MEASURE
COL : 0.100 mm

Ni
양백

SEC : 15 Sec



범위 0.071
평균값 1.476
표준편차 0.028
변동계수 1.874



발행처 : 우리하이피(주)

: 동일메탈

: 0.1X171

종물

LOT NO : 260911-01

DATE : 26.09.11.


No	μm Ni	Ni tolerance	
		1.412	1.444 1.475
1	1.455		
2	1.464		
3	1.412		
4	1.443		
Mean	1.444		
S.Dev	0.023		

FUNC: MEASURE

COL : 0.100 mm

$\frac{\text{Ni}}{\text{양백}}$

SEC : 15 Sec



도금원소 : Ni//양백

측정값 개수 4

최대값 1.464

최소값 1.412

범위 0.052

평균값 1.444

표준편차 0.023

변동계수 1.572

발행처 : 우리하이피(주)

