



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*35	20260903 -01	2026-09-03
규격(재질)		LOT SIZE(수량)	
0.15*35 304 1/2H	Ni 3.0 μ m~	6 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물짐)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		고객		판정
		규격	하한(-)	상한(+)		1차	2차	1차	2차	
1	전폭	35.0	-0.1		Reel/Lot	34.964				OK
2										
3										
4										
5										
6										
7										
8										
9										
10										

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정	Ni 3.0 μ m~	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금들뜸이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	합격 2026-09-03 우리하이피(주) Q.C
		고객	작성	승인		

: 세종에이앤에스


3 : 0.15X35 초물 LOT NO : 260903-01 DATE : 26.09.03.

No	μm Ni	Ni	tolerance
		3.494	3.534 3.575
1	3.525		
2	3.503		
3	3.560		
4	3.509		
5	3.575		
Mean	3.534		
S.Dev	0.032		

FUNC: MEASURE
COL : 0.100 mm


$\frac{Ni}{SS}$

SEC : 15 Sec



도금원소 : Ni//SS
 측정값 개수 5
 최대값 3.575
 최소값 3.503
 범위 0.072
 평균값 3.534
 표준편차 0.032
 변동계수 0.897

우리하이피



: 세종에이앤에스


형 : 0.15X35 종물 LOT NO : 260903-01 DATE : 26.09.03.

No	μm Ni	Ni tolerance
1	3.553	3.509 3.548 3.586
2	3.538	
3	3.563	
4	3.575	
5	3.509	
Mean	3.548	
S.Dev	0.025	

FUNC: MEASURE
COL : 0.100 mm


$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



도금원소 : Ni//SS
측정값 개수 5
최대값 3.575
최소값 3.509
범위 0.066
평균값 3.548
표준편차 0.025
변동계수 0.719

우리하이피



세종에이앤에스


형 : 0.15X35 초물 LOT NO : 260903-01 DATE : 26.09.03.

No	μm Ni	Ni tolerance
1	3.479	3.424 3.459 3.493
2	3.450	
3	3.436	
4	3.493	
5	3.435	
Mean	3.459	
S.Dev	0.026	

FUNC: MEASURE
COL : 0.100 mm


$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



도금원소 : Ni//SS
측정값 개수 5
최대값 3.493
최소값 3.435
범위 0.058
평균값 3.459
표준편차 0.026
변동계수 0.757

우리하이피



: 세종에이앤에스

명 : 0.15X35

종물

LOT NO : 260903-01


DATE : 26.09.03.

No	μm Ni	Ni	tolerance
1	3.505	3.369	3.437 3.505
2	3.398		
3	3.430		
4	3.406		
5	3.446		
Mean	3.437		
S.Dev	0.043		

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



도금원소 : Ni//SS

측정값 개수 5

최대값 3.505

최소값 3.398

범위 0.107

평균값 3.437

표준편차 0.043

변동계수 1.237

우리하이피

