

L1M6080040



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
㈜씨스파인	0.15*117	20260908 -01	2026-09-08
규격(재질)		LOT SIZE(수량)	
0.15*117 304 1/2H	Ni 1.7~3.0μm	140 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(일록)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		고객		판정
		규격	하한(-)	상한(+)		1차	2차	1차	2차	
1	전폭	117.0	-0.1		Reel/Lot	116.928				OK
2										
3										
4										
5										
6										
7										
8										
9										
10										

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정	Ni 1.7~3.0μm	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 밀착후 45도 각 떼어낸다.(돌돌 2.테이프 시험이 니퍼로 90도로 이나 벗겨짐이		

제품도면	0.15*117 117.0	리하이피	김영란	조승현	종합판정	합격 2026-09-08 우리하이피(주) Q.C
		고객	작성	승인	종합판정	

명: (주)씨스파인

품명 : 0.15X117 LOT NO : 260908-01 DATE : 26.09.08.

No	μm Ni	Ni tolerance
1	1.814	1.802 1.849 1.896
2	1.896	
3	1.832	
4	1.844	
5	1.856	
6	1.851	
Mean	1.849	
S.Dev	0.028	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



측정값 개수 6
최대값 1.896
최소값 1.814
범위 0.082
평균값 1.849
표준편차 0.028
변동계수 1.491

우리하이피

