



Quality Assurance Report

BOX NO : L1X6081137

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
(주)씨스파인	0.15*138	20260917 - 01(02)	2026-09-17
규격(재질)		LOT SIZE(수량)	
0.15*138 304 1/2H	Ni 1.7~3.0μm	348 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		고객		판정
		규격	하한(-)	상한(+)		1차	2차	1차	2차	
1	전폭	138.0	-0.1		Reel/Lot	137.997				OK
2										
3										
4										
5										
6										
7										
8										
9										
10										

III. PLATING THICKNESS(도금두께) (Sampling Plan y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.7~3.0μm	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)			
제품 도면			하이피	심문경
			조승현	판정
			작성	승인
				종합판정

우리하이피(주)
Q.C

고객명: (주)씨스파인

품명 : 0.15X138

LOT NO : 260917-01

DATE : 26.09.17


No	μm Ni	Ni tolerance		
		1.829	1.858	1.887
1	1.871			
2	1.836			
3	1.868			
4	1.884			
5	1.829			
6	1.861			
Mean	1.858			
S.Dev	0.021			

FUNC: MEASURE

COL : 0.100 mm

Ni
SS

SEC : 15 Sec



도금원소 : Ni//SS

측정값 개수 6

최대값 1.884

최소값 1.829

범위 0.055

평균값 1.858

표준편차 0.021

변동계수 1.149

우리하이피

