

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코넥	DUMMY-D9385924	20260930-1	2026.09.30
MATERIAL(재질)	SPEC		수량
Al	Nip : 2.0~4.0 μ m		2,140 EA

I. VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II. DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III. FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

에스코백 Nip : 2.0~4.0 μ m


품명 : DUMMY-D9385924 LOT NO : 20260930-1 일자 : 2026.09.30

No	μ m NiP	NiP tolerance		
		2.704	2.844	2.983
1	2.844			
2	2.856			
3	2.909			
4	2.704			
5	2.905			
Mean	2.844			
S.Dev	0.074			

FUNC: MEASURE
DATE: 2026-09-30
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$

SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 2.909

최소값 2.704

범위 0.205

평균값 2.844

표준편차 0.074

변동계수 2.617

발행처 : 우리하이피

