



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
㈜유스틸	0.15*46	20260918 - 01~02	2026-09-18
규격(재질)		LOT SIZE(수량)	
0.15*46 S304 1/2H		210 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(일룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		수량	고객		판정
		규격	하한(-)	상한(+)		1차	2차		1차	2차	
1	전폭	46.0	-0.1		Reel/Lot	45.939		105.0			OK
2						45.970		105.0			
3											
4											
5											
6											
7											
8											
9											
10											

III. PLATING THICKNESS(도금두께) (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상,하각은후 도금들뜸 이나 벗겨짐이 없을것.		

제품도면		우리하이피	심문경	조승현	합판정	
		고객	작성	승인	종합판정	

고객명: (주)유스틸



품명 : 0.15X46 LOT NO : 260917-01 DATE : 26.09.17

No	μm Ni	Ni tolerance
1	2.012	2.001 2.037 2.072
2	2.059	
3	2.011	
4	2.029	
5	2.072	
Mean	2.037	
S.Dev	0.028	


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



도금원소 : Ni//SS
측정값 개수 5
최대값 2.072
최소값 2.011
범위 0.061
평균값 2.037
표준편차 0.028
변동계수 1.361



우리하이피