

Quality Assurance Report (신형)

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
지디에스	SAMPLE	20260930-1	2026.09.30
MATERIAL(재질)	SPEC		수량
A3003-H14	Ni: 1.0~5.0 μ m / Sn: 4.0~10.0 μ m		10 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~5.0 μ m				
12	PLATING THICKNESS (Sn)	4.0~10.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling	PASS	OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

지디에스

Ni: 1.0~5.0 μ m Sn: 4.0~10.0 μ m



품명: SAMPLE LOT NO: 20260930-1 일자: 2026.09.30

No	μ m Sn	μ m Ni	Sn 5.932	tolerance 6.211	6.489
1	6.348	2.058			
2	6.181	2.155			
3	6.008	2.152			
4	6.489	2.142			
5	6.027	2.083			
Mean	6.211	2.118			
S.Dev	0.185	0.040			

FUNC: MEASURE
DATE: 2026-10-01
COL : 0.400 mm

Sn
Ni
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	5	5
최대값	6.489	2.155
최소값	6.008	2.058
범위	0.481	0.097
평균값	6.211	2.118
표준편차	0.185	0.040
변동계수	2.987	1.880

발행처 : 우리하이피

