

제 재	작성 (Prepared)	검토 (Checked)	승인 (Approved)	anbit T&I 검 사 성 적 서 Inspection Report				결 재	작성 (Prepared)	검토 (Checked)	승인 (Approved)
	나우인		조승현								
고객명 (Customer)		한빛티앤아이		품명 (Part Name)	Heat Spreader			납품서NO (Order No.)			
모델 (Model)		18.6mm Body		모델 NO. (Model No.)	0850283HS			관리번호 (Report NO.)			
재질 (Material)				도면 REV.NO							
검사 단계		수입검사		구분 (Classification)	로개발신설 (Development) ☒양산중 ☐설변 ☐금형재제작 ☐기타						
측정 단위 : mm (Measuring Unit : mm)				특기 사항 (Comments)							
				종합 판정 (Judgement)		☒ 적합품 (OK Part) ☐ 부적합품 (NG Part)					
				LOT 크기 (Quantity)		87,750 pcs					
				검사 일자 (Date of Inspection)		2026.09.03.					
				검사원 (Inspector)		우리하이피 나우인					
				측정기 범례	약어 (Abbreviation)	측정기명 (Measuring Instrument)					
					TM	Toolmakers Microscope					
					DC	Digimatic Calipers					
					PG	Pin Gauge					
					RD	reflection densitometer					
MM	Micro Meter										
HG	Height Gauge										
TC	Thickness&Coating Measurement System										
DP	Dyne pen										
순번 (NO)	검사 항목 (Inspection Method)	규격 (Specification)	측정기 (Measuring Instrument)	x1 (Sample 1)	x2 (Sample 2)	x3 (Sample 3)	x4 (Sample 4)	x5 (Sample 5)	Sample SIZE	판정 (Judgement)	
1	외관	일록,변색,이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1	육안	OK	OK	OK	OK	OK	500	OK	
2	도금두께	3.0 ~ 6.0 μ m	TC	3.247	3.268	3.322	3.206	3.239	5	OK	
3	Reflection Density	0.65 ~ 0.95	RD	0.81	0.87	0.85	0.88	0.85	5	OK	
4	에너지펜 TEST NO.36	균질,웅침없을것	DP	OK	OK	OK	OK	OK	5	OK	
5	CROSS Cutting	개별 격자 1mm 이 내 20% 이하일것	육안	OK	OK	OK	OK	OK	5	OK	
6											
7											
8											

한빛티앤아이


부품명 : Heat Spreader 18.6mm 0.5T LOT NO : 260903-01 DATE : 26.09.03.

No	μm Ni	
1	3.247	
2	3.268	
3	3.322	
4	3.206	
5	3.239	
Mean	3.256	
S.Dev	0.043	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 3.322
최소값 3.206
범위 0.116
평균값 3.256
표준편차 0.043
변동계수 1.318

우리하이피(주)

