

재	작성 (Prepared)	검토 (Checked)	승인 (Approved)	Hanbit T&I	검 사 성 적 서 Inspection Report				재	작성 (Prepared)	검토 (Checked)	승인 (Approved)
	나우인		조승현									
고객명 (Customer)		한빛티앤아이		품명 (Part Name)	Heat Spreader				납품서NO (Order No.)			
모델 (Model)		18.6mm Body		모델 NO. (Model NO.)	0850283HS				관리번호 (Report NO.)			
재질 (Material)				도면 REV.NO								
검사 단계		수입검사		구분 (Classification)	☐ 개발신설 (Development) ☒ 양산중 (Production) ☐ 설변 (Design Change) ☐ 금형재제작 (Mold Rebuild) ☐ 기타 (Etc)							
측정 단위 : mm (Measuring Unit : mm)					특기 사항 (Comments)							
					종합 판정 (Judgement)		☒ 적합품 (OK Part) ☐ 부적합품 (NG Part)					
					LOT 크기 (Quantity)		72,150 pcs					
					검사 일자 (Date of Inspection)		2026.09.10.					
					검사원 (Inspector)		우리하이피 나우인					
					측정기 범례	약어 (Abbreviation)	측정기명 (Measuring Instrument)					
						TM	Toolmakers Microscope					
						DC	Digimatic Calipers					
						PG	Pin Gauge					
						RD	reflection densitometer					
MM	Micro Meter											
HG	Height Gauge											
TC	Thickness&Coating Measurement System											
DP	Dyne pen											
순번 (NO)	검사 항목 (Inspection Method)	규격 (Specification)	측정기 (Measuring Instrument)	x1 (Sample 1)	x2 (Sample 2)	x3 (Sample 3)	x4 (Sample 4)	x5 (Sample 5)	Sample SIZE	판정 (Judgement)		
1	외관	압록,변색,이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1	육안	OK	OK	OK	OK	OK	500	OK		
2	도금두께	3.0 ~ 6.0 μm	TC	3.310	3.291	3.313	3.330	3.380	5	OK		
3	Reflection Density	0.65 ~ 0.95	RD	0.82	0.88	0.87	0.86	0.83	5	OK		
4	에너지펜 TEST NO.36	긁김,뭉침없을것	DP	OK	OK	OK	OK	OK	5	OK		
5	CROSS Cutting	개별 격자 1mm 이 내 20% 이하일것	육안	OK	OK	OK	OK	OK	5	OK		
6												
7												
8												

고객명: 한빛티앤아이

품명 : Heat Spreader 18.6mm 0.5T LOT NO : 260910-01 DATE : 26.09.10



No	μm Ni	Ni tolerance
1	3.310	3.270 3.325 3.380
2	3.291	
3	3.313	
4	3.330	
5	3.380	
Mean	3.325	
S.Dev	0.034	

FUNC: MEASURE

COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 3.380

최소값 3.291

범위 0.089

평균값 3.325

표준편차 0.034

변동계수 1.017

우리하이피(주)

