

결재	작성 (Prepared)	검토 (Checked)	승인 (Approved)	Hanbit T&I				검 사 성 적 서 Inspection Report				결재	작성 (Prepared)	검토 (Checked)	승인 (Approved)
고객명 (Customer)	한빛티앤아이			품명 (Part Name)	Heat Spreader				납품서NO (Order No.)						
모델 (Model)	18.6mm Body			모델 NO. (Model NO.)	0850283HS				관리번호 (Report NO.)						
재질 (Material)				도면 REV.NO											
검사 단계	수입검사			구분 (Classification)	☐ 개발신설 (Development) ☒ 양산중 (Production) ☐ 설변 (Design Change) ☐ 금형재제작 (Mold Rebuilt) ☐ 기타 (Etc)										
측정 단위 : mm (Measuring Unit : mm)					특기 사항 (Comments)										
					종합 판정 (Judgement)		☒ 적합품 (OK Part) ☐ 부적합품 (NG Part)								
					LOT 크기 (Quantity)		70,470 pcs								
					검사 일자 (Date of Inspection)		2026.09.11.								
					검사원 (Inspector)		우리하이피 심문경								
					측정기 편례	약어 (Abbreviation)	측정기명 (Measuring Instrument)								
						TM	Toolmakers Microscope								
						DC	Digimatic Calipers								
						PG	Pin Gauge								
						RD	reflection densitometer								
MM	Micro Meter														
HG	Height Gauge														
TC	Thickness&Coating Measurement System														
DP	Dyne pen														
순번 (NO)	검사항목 (Inspection Method)	규격 (Specification)	측정기 (Measuring Instrument)	x1 (Sample 1)	x2 (Sample 2)	x3 (Sample 3)	x4 (Sample 4)	x5 (Sample 5)	Sample SIZE	판정 (Judgement)					
1	외관	얼룩, 변색, 이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1	육안	OK	OK	OK	OK	OK	500	OK					
2	도금두께	3.0 ~ 6.0 μm	TC	3.252	3.243	3.307	3.206	3.328	5	OK					
3	Reflection Density	0.65 ~ 0.95	RD	0.84	0.81	0.83	0.84	0.81	5	OK					
4	에너지펜 TEST NO.36	긁김, 뭉침없을것	DP	OK	OK	OK	OK	OK	5	OK					
5	CROSS Cutting	개별 격자 1mm 이 내 20% 이하일것	육안	OK	OK	OK	OK	OK	5	OK					
6															
7															
8															

고객명: 한빛티앤아이



품명 : Heat Spreader 18.6mm 0.5T LOT NO : 260911-01 DATE : 26.09.11

No	μm Ni	Ni tolerance	
		3.206	3.267 3.328
1	3.252		
2	3.243		
3	3.307		
4	3.206		
5	3.328		
Mean	3.267		
S.Dev	0.050		

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 3.328

최소값 3.206

범위 0.122

평균값 3.267

표준편차 0.050

변동계수 1.518

우리하이피(주)

