

재	작성 (Prepared)	검토 (Checked)	승인 (Approved)	anbit T&I	검 사 성 적 서 Inspection Report		재	작성 (Prepared)	검토 (Checked)	승인 (Approved)																																																																																																			
	심묵경		조승현																																																																																																										
고객명 (Customer)		한빛티앤아이		품명 (Part Name)		Heat Spreader		납품서NO (Order No.)																																																																																																					
모델 (Model)		23mm BD 0.5T		모델 NO. (Model NO.)		0850509HS		관리번호 (Report NO.)																																																																																																					
재질 (Material)				도면 REV.NO																																																																																																									
검사 단계		수입검사		구분 (Classification)		☐ 개발신설 (Development) ☒ 양산중 (Production) ☐ 설변 (Design Change) ☐ 금형재제작 (Mold Rebuilt) ☐ 기타 (Etc)																																																																																																							
MODEL HISTORY <table border="1"> <tr> <th>NO</th> <th>DESCRIPTION</th> <th>DATE</th> </tr> <tr> <td>A</td> <td>INITIAL REVIEW</td> <td>05/22/21</td> </tr> <tr> <td>B</td> <td>CHANGED (DATE) SIZE TO 18mm FROM 17mm</td> <td>05/27/21</td> </tr> </table> 특기 사항 (Comments)				NO	DESCRIPTION	DATE	A	INITIAL REVIEW	05/22/21	B	CHANGED (DATE) SIZE TO 18mm FROM 17mm	05/27/21	종합 판정 (Judgement) LOT 크기 (Quantity) 검사 일자 (Date of Inspection) 검사원 (Inspector)				☒적합품 (OK Part) ☐부적합품 (NG Part) 55,100 pcs 2026.09.22. 우리하이피 심묵경																																																																																												
NO	DESCRIPTION	DATE																																																																																																											
A	INITIAL REVIEW	05/22/21																																																																																																											
B	CHANGED (DATE) SIZE TO 18mm FROM 17mm	05/27/21																																																																																																											
측정 단위 : mm (Measuring Unit : mm)				측정기 (Measuring Instrument) <table border="1"> <tr> <th>약어 (Abbreviation)</th> <th>측정기명 (Measuring Instrument)</th> </tr> <tr> <td>TM</td> <td>Toolmakers Microscope</td> </tr> <tr> <td>DC</td> <td>Digimatic Calipers</td> </tr> <tr> <td>PG</td> <td>Pin Gauge</td> </tr> <tr> <td>RD</td> <td>reflection densitometer</td> </tr> <tr> <td>MM</td> <td>Micro Meter</td> </tr> <tr> <td>HG</td> <td>Height Gauge</td> </tr> <tr> <td>TC</td> <td>Thickness&Coating Measurement System</td> </tr> <tr> <td>DP</td> <td>Dyne pen</td> </tr> </table>				약어 (Abbreviation)	측정기명 (Measuring Instrument)	TM	Toolmakers Microscope	DC	Digimatic Calipers	PG	Pin Gauge	RD	reflection densitometer	MM	Micro Meter	HG	Height Gauge	TC	Thickness&Coating Measurement System	DP	Dyne pen																																																																																				
약어 (Abbreviation)	측정기명 (Measuring Instrument)																																																																																																												
TM	Toolmakers Microscope																																																																																																												
DC	Digimatic Calipers																																																																																																												
PG	Pin Gauge																																																																																																												
RD	reflection densitometer																																																																																																												
MM	Micro Meter																																																																																																												
HG	Height Gauge																																																																																																												
TC	Thickness&Coating Measurement System																																																																																																												
DP	Dyne pen																																																																																																												
하단은 고객 기록란 <table border="1"> <thead> <tr> <th>순번 (NO)</th> <th>검사 항목 (Inspection Method)</th> <th>규격 (Specification)</th> <th>측정기 (Measuring Instrument)</th> <th>x1 (Sample 1)</th> <th>x2 (Sample 2)</th> <th>x3 (Sample 3)</th> <th>x4 (Sample 4)</th> <th>x5 (Sample 5)</th> <th>Sample SIZE</th> <th>판정 (Judgement)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>외관</td> <td>일록,변색,이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1</td> <td>육안</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>500</td> <td>OK</td> </tr> <tr> <td>2</td> <td>도금두께</td> <td>3.0 ~ 6.0 μm</td> <td>TC</td> <td>3.291</td> <td>3.214</td> <td>3.262</td> <td>3.165</td> <td>3.295</td> <td>5</td> <td>OK</td> </tr> <tr> <td>3</td> <td>Reflection Density</td> <td>0.65 ~ 0.95</td> <td>RD</td> <td>0.83</td> <td>0.81</td> <td>0.85</td> <td>0.83</td> <td>0.81</td> <td>5</td> <td>OK</td> </tr> <tr> <td>4</td> <td>에너지펜 TEST NO.36</td> <td>끊김,용침없을것</td> <td>DP</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>5</td> <td>OK</td> </tr> <tr> <td>5</td> <td>CROSS Cutting</td> <td>개별 격자 1mm 이내 20% 이하일것</td> <td>육안</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>OK</td> <td>5</td> <td>OK</td> </tr> <tr> <td>6</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>7</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>8</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> </tbody> </table>											순번 (NO)	검사 항목 (Inspection Method)	규격 (Specification)	측정기 (Measuring Instrument)	x1 (Sample 1)	x2 (Sample 2)	x3 (Sample 3)	x4 (Sample 4)	x5 (Sample 5)	Sample SIZE	판정 (Judgement)	1	외관	일록,변색,이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1	육안	OK	OK	OK	OK	OK	500	OK	2	도금두께	3.0 ~ 6.0 μm	TC	3.291	3.214	3.262	3.165	3.295	5	OK	3	Reflection Density	0.65 ~ 0.95	RD	0.83	0.81	0.85	0.83	0.81	5	OK	4	에너지펜 TEST NO.36	끊김,용침없을것	DP	OK	OK	OK	OK	OK	5	OK	5	CROSS Cutting	개별 격자 1mm 이내 20% 이하일것	육안	OK	OK	OK	OK	OK	5	OK	6											7											8										
순번 (NO)	검사 항목 (Inspection Method)	규격 (Specification)	측정기 (Measuring Instrument)	x1 (Sample 1)	x2 (Sample 2)	x3 (Sample 3)	x4 (Sample 4)	x5 (Sample 5)	Sample SIZE	판정 (Judgement)																																																																																																			
1	외관	일록,변색,이물 없을것 KS A ISO 2859-1 일반검사 수준 G-2 AQL=0.1	육안	OK	OK	OK	OK	OK	500	OK																																																																																																			
2	도금두께	3.0 ~ 6.0 μm	TC	3.291	3.214	3.262	3.165	3.295	5	OK																																																																																																			
3	Reflection Density	0.65 ~ 0.95	RD	0.83	0.81	0.85	0.83	0.81	5	OK																																																																																																			
4	에너지펜 TEST NO.36	끊김,용침없을것	DP	OK	OK	OK	OK	OK	5	OK																																																																																																			
5	CROSS Cutting	개별 격자 1mm 이내 20% 이하일것	육안	OK	OK	OK	OK	OK	5	OK																																																																																																			
6																																																																																																													
7																																																																																																													
8																																																																																																													

고객명: 한빛티앤아이

품명 : Heat Spreader (23mm 0.5T)

LOT NO : 260922-01


DATE : 26.09.22

No	μm Ni	Ni tolerance		
		3.165	3.245	3.326
1	3.291			
2	3.214			
3	3.262			
4	3.165			
5	3.295			
Mean	3.245			
S.Dev	0.055			

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 3.295

최소값 3.165

범위 0.130

평균값 3.245

표준편차 0.055

변동계수 1.706

우리하이피(주)

