

A Step towards the Origin of Fracture

Samuel Walker

A Thesis presented for the degree of
Doctor of Philosophy



Department of Physics
Durham University
United Kingdom
March 2026

Contents

1	Introduction	1
1.1	Layout of thesis	1
2	Background	2
2.1	Semi-Flexible filaments	2
2.2	Rigidity	4
2.3	Athermal Fracture	4
2.4	Thermal Fracture	4
2.5	Network Structure	4
	Bibliography	5

Notes

■ Might be worth doing a plot here where we plot change f 4

CHAPTER 1

Introduction

1.1 Layout of thesis

CHAPTER 2

Background

2.1 Semi-Flexible filaments

Biopolymers can be separated into three categories by the ratio of their persistence length l_p to their relevant contour length l_c (in the case of networks the relevant length is the average length between crosslinks). The persistence length is a measure of the rigidity of the polymer and defines the length at which the polymer's orientation remains correlated. Therefore, the persistence length of a polymer can be intuitively thought of as the length at which thermal energy, $k_B T$, is large enough to have an effect on the direction of the polymer (formally defined as the length at which the correlation between the two tangent equals $1/e$) and can be defined by $l_p = \kappa/(k_B T)$.

For short or stiff polymers where $l_p \ll l_c$ the polymer acts like a rigid rod with its mechanical response governed by the polymer's stretching of molecular bonds. Polymers where $l_p \gg l_c$ take a naturally folded state as the thermal energy is sufficient to bend the filament significantly, these polymers have mechanical responses driven by entropy where the initial response is governed by the reduction of accessible conformations as the polymer unfolded, followed by a regime governed by the

stretching of molecular bonds as in the stiff case. Semiflexible polymers therefore constitute an intermediate state between the two where their persistence length l_p is large enough relative to their contour length l_c to avoid collapsing into a random coil but large enough that thermally induced bending remains relevant.

The standard model for polymers is the extensible worm-like chain, where each polymer is treated as a homogeneous cylindrical elastic rod with radius r and Young's modulus E [1]. As such the stretching rigidity of the rod can be expressed in terms of the product of its Young's modulus and cross-sectional area $\mu = E\pi r^2$ and its bending rigidity in terms of its Young's modulus and moment of inertia $\kappa = EI = E\pi r^4/4$. We therefore write the Hamiltonian of a single filament as the sum of two integrals

$$\mathcal{H}_f = \frac{\mu}{2} \int ds \left(\frac{dl}{ds} \right)^2 + \frac{\kappa}{2} \int ds \left| \frac{\partial \vec{t}}{\partial s} \right|^2 \quad (2.1)$$

where s is the arc length coordinate, dl/ds is the relative strain of the polymer at point s and $\vec{t}$ is the tangent vector to the polymer. We neglect any energy contributions from the polymers twisting along their axis. This continuum model can be discretised, such that we discrete extensible worm-like chains [2] for which the Hamiltonian of each segment can be expressed as

$$\mathcal{H}_f = \frac{\mu}{2} \sum_{ij} \frac{(l_{ij} - l_{ij,0})^2}{l_{ij,0}} + \frac{\kappa}{2} \sum_{ijk} \frac{(\theta_{ijk} - \theta_{ijk,0})^2}{l_{ijk,0}} \quad (2.2)$$

where the first sum is taken over all pairs ij and triplets ijk along the polymer length. We define l_{ij} and $l_{ij,0}$ as the instantaneous and natural length between nodes i and j respectively, θ_{ijk} and $\theta_{ijk,0}$ to be the instances and natural angle between nodes i , j and k , respectively, and $l_{ijk,0} = (l_{ij,0} + l_{jk,0})/2$. In all cases, we consider a central force model only where bending rigidity is neglected, this can be thought of as the polymers having a small cross-sectional area relative to their length such that their moment of inertia is neglectable compared to their cross-section area

2.2 Rigidity

2.3 Athermal Fracture

2.4 Thermal Fracture

2.5 Network Structure

Network structures generated from jammed disk or sphere packing have been extensively to study elastic or fibre networks [3–8].

The Jammed packing networks are generated by distributing N disks with bidispersed radii in a square periodic box with side length L . An equal number of disks are chosen to have either a radii R_0 or fR_0 where f is chosen to take a value which reduces crystallisation in the system.

Might be worth doing a plot here where we plot change f

A common value and the one used to generate any networks presented in this work is $f = 1.4$ [9, 10]

Bibliography

- [1] M. Doi et al. *The Theory of Polymer Dynamics*. International Series of Monographs on Physics. Oxford, New York: Oxford University Press, Nov. 1988.
- [2] F. C. MacKintosh, J. Käs, and P. A. Janmey. “Elasticity of Semiflexible Biopolymer Networks”. In: *Physical Review Letters* 75.24 (Dec. 1995). Publisher: American Physical Society, pp. 4425–4428.
- [3] R. Rens and E. Lerner. “Rigidity and auxeticity transitions in networks with strong bond-bending interactions”. en. In: *The European Physical Journal E* 42.9 (Sept. 2019), p. 114.
- [4] M. Wyart et al. “Elasticity of Floppy and Stiff Random Networks”. en. In: *Physical Review Letters* 101.21 (Nov. 2008), p. 215501.
- [5] E. Lerner, G. Düring, and M. Wyart. “A unified framework for non-Brownian suspension flows and soft amorphous solids”. In: *Proceedings of the National Academy of Sciences* 109.13 (Mar. 2012). Publisher: Proceedings of the National Academy of Sciences, pp. 4798–4803.
- [6] J. L. Shivers et al. “Normal stress anisotropy and marginal stability in athermal elastic networks”. en. In: *Soft Matter* 15.7 (2019), pp. 1666–1675.
- [7] J. L. Shivers et al. “Scaling Theory for Mechanical Critical Behavior in Fiber Networks”. In: *Physical Review Letters* 122.18 (May 2019). Publisher: American Physical Society, p. 188003.
- [8] J. L. Shivers. “Phase transitions in the rheology of biopolymer networks”. eng. Accepted: 2022-07-14T16:53:37Z. Thesis. Rice University, Mar. 2022.
- [9] M. van Hecke. “Jamming of soft particles: geometry, mechanics, scaling and isostaticity”. en. In: *Journal of Physics: Condensed Matter* 22.3 (Jan. 2010), p. 033101.
- [10] R. N. Chacko, P. Sollich, and S. M. Fielding. “Slow Coarsening in Jammed Athermal Soft Particle Suspensions”. en. In: *Physical Review Letters* 123.10 (Sept. 2019), p. 108001.