

Laboratory Report Fresco Colors Research
Project: Intumescent Coating Development

Experiment EXP-004 was repeated under modified conditions.
Adhesion measured at 89.
Expansion ratio: 22.0.
APP = 30.

Note: These measurements were taken after a 30-day aging period.
The results indicate that aging reduces adhesion performance significantly.