

OSP Cable - Optical Characteristics - G.655.C & G.655.D OFS TWRS

This specification covers fibre characteristics for Coloured OFS TWRS Non-Zero Dispersion Shifted Single-mode ITU-T Rec. G.655.C & G.655.D in LT designs manufactured at the AFL Australia facility.

NZDS G.655.C & G.655.D SINGLE-MODE FIBRE		
FIBRE SPECIFICATION (FIBRE CODE DESIGNATOR)		G.655.C & G.655.D (RS)
STRUCTURAL		
Typical Mode Field Diameter	@1550 nm	$8.4 \pm 0.6 \mu\text{m}$
Cladding Diameter		$125 \pm 0.7 \mu\text{m}$
Max. Mode Field Concentricity Error		$0.5 \mu\text{m}$
Coating-Cladding Concentricity Error		$\leq 12 \mu\text{m}$
Cladding Non-circularity		$\leq 0.7\%$
Fibre Coating Diameter (Uncoloured)		$242 \pm 5 \mu\text{m}$
OPTICAL		
Max. Attenuation (Cabled)	@1310 nm	0.41 dB/km
	@1550 nm	0.23 dB/km
	@1625 nm	0.25 dB/km
Group Refractive Index	@1550 nm	1.470
100 Turns, 60 mm Diameter	@1550 nm	$\leq 0.05 \text{ dB}$
	@1625 nm	$\leq 0.05 \text{ dB}$
Max. Cut-off Wavelength (λ_{cc})		1260 nm
Max. Point Discontinuity at 1550 nm (Cabled)		$\leq 0.1 \text{ dB}$
Disp. Slope at 1550 nm		$\leq 0.05 \text{ (ps/nm}^2\text{.km)}$
Ch. Disp. Coefficient	@1530 – 1565 nm	$\leq 2.6 - 6.0 \text{ ps/(nm.km)}$
	@1565 – 1625 nm	$\leq 4.0 - 8.9 \text{ ps/(nm.km)}$
	@1460 – 1625 nm	$- 1.0 - 8.9 \text{ ps/(nm.km)}$
PMD Ind.Fibre/LDV		$\leq 0.1 / \leq 0.04 \text{ (ps}/\sqrt{\text{km}}\text{)}$
MECHANICAL		
Proof Test		$\geq 1 \% (100 \text{ kpsi}/0.7 \text{ GPa})$
Strip Force (F)		$1.0 \text{ N} \leq F \leq 8.9 \text{ N}$

FIBRE IDENTIFICATION	
Fibre Colour Sequence	Blue, Orange, Green, Brown, Grey, White, Red, Black, Yellow, Violet, Pink, Aqua

This datasheet is provided for guidance only and is subject to change without notice. Please ensure you have the most up to date information where parameters in this document are considered critical for your particular application.