

Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

Date: 07/02/2023

Ref. No.: REC/CED/070223/07

TEST REPORT

Departmental Consultancy No.- CE/668

Sample: Cement Concrete Cube

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division-Baharaich (U.P.).

Name of Work: जनपद श्रावस्ती के न्यायालय परिसर में फैमिली कोर्ट का निर्माण कार्य।

Reference: 588/बहो/यूपीआरएनएसएस/2022-23/SR-31, Dated: 24.01.2023

Tested for: Compressive Strength

Tested as per: IS 456:2000, IS 516:1959

No. of Sample: One set only.

TEST RESULTS

Specimen No.	Age (Days)	Crushing Load (kN)	Area (mm ²)	Compressive Strength (N/mm ²)	Average Compressive Strength (N/mm ²)
1.	28	625	22500	27.78	27.26
2.	28	605	22500	26.89	
3.	28	610	22500	27.11	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Pooja Pathak)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator