



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

Ref. No.: REC/CED/190922/04

Date: 19/09/2022

TEST REPORT

Departmental Consultancy No.: CE/501

Sample: Cement Concrete Cube

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division-Gonda-II, Gonda (U.P.).

Name of Work: फैमिली कोर्ट जनपद श्रावस्ती के निर्माण कार्य में प्रयोग की जाने वाली सामग्री का परीक्षण।

Reference: 315/ बहो/ यू पी 0 आर 0 एन 0 एस 0 एस 0 /2022-23/ SR-31, Dated: 11.08.2022

Tested for: Compressive Strength

Tested as per: IS 456:2000, IS 516:1959

No. of Sample: One set Only

TEST RESULTS


Specimen No.	Age (days)	Crushing Load (kN)	Area (mm ²)	Compressive Strength	Average Compressive
1.	28	610	22500	27.11	26.44
2.	28	590	22500	26.22	
3.	28	585	22500	26.00	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Anupam Kumar Verma)
Lab. Staff


(Amit Kr. Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator