



Agrawal Associates

Building Planners, Valuer, Surveyor, Structural
Designers, Soils & Material Testing etc.



AN ISO 9001 &
ANABL CERTIFIED CO.

Diwan Bazar (New Colony)
Gorakhpur (U.P.) - 273001
Mobile : 9935436083
email : arjun.agarwal1964@gmail.com
www : soilsurveying.com

Our Clients : GDA, Railway, BSNL, U.P.P.C.L., Jal Nigam, L&T, UPRNN, UPRNSS

Ref. No. ...AA-255.....

Date 08.08.2022.....Page 1

TESTING REPORT

Name of Dept. : Executive Engineer
UPRNSS
Construction Division
Gorakhpur 1st
Order No : 577/Construction /Material test/2022-23 Dated 04.08.2022
Name of work : Building Animal hospital Deoria
Sample Received : (01) Fine Aggregate (Coarse Sand)
(02&3) Coarse Aggregate (20mm & 40 Stone Ballast)
(04) Brick

RESULTS

1st Coarse Sand

SIEVE ANALYSIS

Total Weight -1000gm

Size of Sieve	Wt. retained in gm	% wt. retained	Cumulative % retained	% of passing	Grading limit for coarse sand (zone II) According to I.S.383-1961
10mm	---	---	---	100	100%
4.75 mm	77	8.20	8.20	93.40	90-100%
2.36 "	78	7.80	16.00	84.00	75-100%
1.18 "	170	17.00	33.00	67.00	55-90%
600 μ	165	16.50	49.50	50.50	35-59%
300 "	345	34.50	84.00	16.00	8-30%
150 "	140	14.00	98.00	2.00	0-10%

FM-2.82

Coarse Sand Followed Grading Zone - II

2nd Coarse Aggregate (20mm Stone Ballast) -

SIEVE ANALYSIS


Total Weight -4000gm

Size of Sieve in mm	Wt. retained in gm	% wt. retained	Cumulative % retained	% of passing	Grading limit for 20.00mm Graded Agg. according to I.S.383-1961.
63	---	---	---	---	---
40.00	---	---	---	100	100%
20.00	200	5.00	5.00	95.00	95-100%
10.00	2050	51.25	56.25	43.75	25-55%
4.75	1750	43.75	100.00	---	0-10%

Flakiness index, Crushing value, Presence of deleterious material

Results

Sl. NO	Name of test	Results
01	Flakiness index in %age	15.10%
02	Crushing Value	12.10%
03	Presence of deleterious materials	2.50%





Agrawal Associates

Building Planners, Valuer, Surveyor, Structural
Designers, Soils & Material Testing etc.



AN ISO 9001 &
ANABL CERTIFIED CO.

Diwan Bazar (New Colony)

Gorakhpur (U.P.) - 273001

Mobile : 9935436083

email : arjun.agarwal1964@gmail.com

www : soilsurveying.com

Our Clients : GDA, Railway, BSNL, U.P.P.C.L., Jal Nigam, L&T, UPRNN, UPRNSS

Ref. No.

Date.....Page 2

3rd Coarse Aggregate (20mm Stone Ballast) -

Total Weight 4000gm

Size of Sieve in mm	Wt. retained in gm	% wt. retained	Cumulative % retained	% of passing	Grading limit for 40.00mm According I.S.383-1961
80	---	---	---	---	100
63	---	---	---	---	---
40	120	3.00	3.00	97.00	95-100
20	2470	61.75	64.75	35.25	30-70
10	960	24.00	88.75	11.25	10-35
4.75	450	11.25	100.00	00	0-5

Flakiness index, Crushing value, Presence of deleterious material

Results

Sl. NO	Name of test	Results
01	Flakiness index in %age	8.10%
02	Crushing Value	13.10%
03	Presence of deleterious materials	1.50%

04 Brick Brand DEV

Sl. No.	Specimen	Crushing strength in kg /cm ²	Water absorption in %	Efflorescence
01	1 st	152.50	11.10	Nil
	2 nd	151.60	13.20	Nil
	3 rd	153.70	12.90	Nil
	Average	152.60kg /cm ²	12.40%	Nil

Brick tests are conducted as per I.S. 3495-1976.

Above results are for sample supplied by party mentioned.

S.S.L. Gupta

Er. S.S.L. Gupta

B.E. (Civil)

Ex. Principal

M.P. Polytechnic, G.K.P.

