



☎:2255551

Maharana Pratap Polytechnic

GORAKHPUR

Ref. No.

Date.

MEC/CIVIL /HWY SL2015A

26.07.2022

TESTING REPORT

Source : Executive Engineer
UPRNSS, Construction Div.
Gorakhpur Second

Ref. letter No. : 24 / निर्माण / सामग्री परिक्षण / दिनांक-07.04.2022

Sample Received : Coarse Sand ,Brick, Cement, Cube

RESULTS

1st Coarse Sand –

Total Wt. 1000gm

Size of Sieve	Wt. retained in gm	% wt. retained	Cumulative % retained	% of passing	Grading limit for coarse sand (zone II) According to I.S.383-1961
10mm	---	---	---	100	100%
4.75 mm	75	7.00	7.00	93.00	90-100%
2.36 "	65	6.50	13.50	86.50	75-100%
1.18 "	170	17.00	30.50	69.50	55-90%
600 μ	175	17.50	48.00	52.00	35-59%
300 "	360	36.00	84.00	16.00	8-30%
150 "	160	16.00	100.00	00	0-10%

F.M.=2.83

Coarse Sand Followed Grading Zone - II

2nd Bricks(Size-9''x4.5''x3'')Inch

Makes	Specimen	Brick Crushing strength in kg /cm ²
M.B.F	1 st	151.20
	2 nd	153.30
	3 rd	152.40

3rd Cement – ACC

Sl. No.	Name of test	Results
1	Fineness	4.10%
2	Initial setting time(min)	50minutes
3	Final setting time(max)	4.25Hours



☎:2255551

Maharana Pratap Polytechnic

GORAKHPUR

Ref. No.

Date.

4th Cube(150x150x150)mm

Sr.no	Sample no	Grade	Compressive Strength in N/mm ² (Mpa) After 28 days
01	1 st	M-20	22.70
	2 nd		23.50
	3 rd		22.80

Test results are for sample supplied by party mentioned.

Counter Sign.

P.singh
Principal
M.P.Polytechnic

प्रधानाचार्य
महाराणा प्रताप पालीटेक्निक
गोरखपुर

A.K.Agrawal
A.M.I.E. civil
Lecturer
Civil Engg. Deptt
M.P.Polytechnic ,GKP