



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

Ref. No.: REC/CED/180225/01

Date: 18 / 01 / 2025

TEST REPORT

Departmental Consultancy No.- CE/2138

Sample: Burnt Clay Brick

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division -Basti (U.P.)

Name of Work: जनपद-संतकबीरनगर स्पोर्ट्स स्टेडियम में निर्मित खेल अवस्थापनाओं के जीर्णोद्धार कार्य।

Reference: 617 / प्रखण्ड-बस्ती / सामग्री परीक्षण / 2024-25 **Dated:** 20/01/2025

Tested for: Physical Properties

Tested as per: IS 1077:1992, IS 3495:1992, IS 5454:1976

No. of Sample: One set only.

Identification Mark: LBF

TEST RESULTS

Sr. No.	Frog Mark	Examination of General Quality	Average Compressive Strength (N/mm ²)
1.	LBF	The bricks are free from cracks & flaws, have smooth rectangular faces with sharp corners, are uniform in colour.	15.43

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Pooja Pathak)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

TEST REPORT

Departmental Consultancy No.: CE/2138

Sample: Cement Concrete Cube

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division -Basti (U.P.)

Name of Work: जनपद-संतकबीरनगर स्पोर्ट्स स्टेडियम में निर्मित खेल अवस्थापनाओं के जीर्णोद्धार कार्य।

Reference: 617/प्रखण्ड-बस्ती/सामग्री परीक्षण/2024-25 **Dated:** 20/01/2025

Tested for: Compressive Strength

Tested as per: IS 456:2000, IS 516:1959

No. of Sample: Two sets.

TEST RESULTS

Specimen No.	Age (Days)	Crushing Load (kN)	Area (mm ²)	Compressive Strength (N/mm ²)	Average Compressive Strength (N/mm ²)
1.	07	355	22500	15.78	17.04
2.	07	415	22500	18.44	
3.	07	380	22500	16.89	
4.	28	605	22500	26.89	24.89
5.	28	560	22500	24.89	
6.	28	515	22500	22.89	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Pooja Pathak)
Lab. Staff


(Amit Kr. Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

TEST REPORT

Departmental Consultancy No.- CE/2138

Sample: Coarse Aggregate (Stone Grit)

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division -Basti (U.P.)

Name of Work: जनपद-संतकबीरनगर स्पोर्ट्स स्टेडियम में निर्मित खेल अवस्थापनाओं के जीर्णोद्धार कार्य।

Reference: 617/प्रखण्ड-बस्ती/सामग्री परीक्षण/2024-25 **Dated:** 20/01/2025

Tested for: Sieve Analysis & Fineness Modulus

Tested as per: IS:2386 (Part-I)- 1963

No. of Sample: One no of Coarse Aggregate

Identification Mark: N/A

TEST RESULTS

Coarse Aggregate (Stone Grit 20 mm nominal size)

S. No.	I.S. Sieve Designation	% Passing by Weight
1.	40 mm	100.0
	20 mm	91.8
	10 mm	45.7
	4.75 mm	3.0
2.	Fineness Modulus = 6.60	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Pooja Pathak)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator