



Department of Civil Engineering
Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122

Ref. No. REC/CE0/300925/05

Date: 30/09/2025

TEST REPORT

Sample: Burnt Clay Brick

Source of Sample: अधिशासी अभियंता, उ०प्र० राज्य निर्माण सहकारी संघ लि०, प्रखण्ड-बस्ती

Name of Work: राजकीय औद्योगिक प्रशिक्षण संस्थान मनिकौरा, सिद्धार्थनगर का अवशेष निर्माण कार्य।

Reference: 320/बस्ती-प्रखण्ड /2025-26 **Date:** 14/08/2025

Tested as per: IS: 3495 Part-1 1992 IS 1077:1992

Marka: K.B.F.

TEST RESULTS

Sr. No.	Examination of General Quality	Average Compressive Strength (N/mm ²)
1.	The bricks are free from cracks & flaws, have smooth rectangular faces with sharp corners, are uniform in color.	16.23

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.

Nitin Kumar Shukla
Assistant Professor
Nitin Kumar Shukla
Asst. Professor, CED
REC Ambedkar Nagar

Dr. Ayush Mittal
Assistant Professor
Dr. Ayush Mittal
Asst. Professor, CED
REC Ambedkar Nagar



Department of Civil Engineering
Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122

Ref. No.: REC/CED/300925/05

Date: 30/08/2025

TEST REPORT

Sample: Mortar

Source of Sample: अधिशासी अभियंता, उ०प्र० राज्य निर्माण सहकारी संघ लि०, प्रखण्ड-बस्ती

Name of Work: राजकीय औद्योगिक प्रशिक्षण संस्थान मनिकौरा, सिद्धार्थनगर का अवशेष निर्माण कार्य।

Reference: 320/बस्ती-प्रखण्ड/2025-26

Date: 14/08/2025

Tested for: Physical Properties

Tested as per: IS: 2250-1981, IS:1905-1987

TEST RESULTS

S.No.	Work	Average Ratio Cement: Sand
1.	Mortar (Cement and Sand)	1: 6.05

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.

Nitin Kumar Shukla

Assistant Professor

Nitin Kumar Shukla

Asst. Professor, CED

REC Ambedkar Nagar

Dr. Ayush Mittal

Assistant Professor

Dr. Ayush Mittal

Asst. Professor, CED

REC Ambedkar Nagar



Department of Civil Engineering
Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122

Ref. No.: REC/CED/300925/05

Date: 30/09/2025

TEST REPORT

Sample: Cement Concrete Cube

Source of Sample: अधिशासी अभियंता, उ०प्र० राज्य निर्माण सहकारी संघ लि०, प्रखण्ड-बस्ती

Name of Work: राजकीय औद्योगिक प्रशिक्षण संस्थान मनिकौरा, सिद्धार्थनगर का अवशेष निर्माण कार्य।

Reference: 320/बस्ती-प्रखण्ड/2025-26

Date: 14/08/2025

Tested for: Compressive Strength

Tested as per: IS 456:2000, IS 516:1959

TEST RESULTS

Specimen No.	Crushing Load (kN)	Area (mm ²)	Compressive Strength (N/mm ²)	Average Compressive Strength (N/mm ²)
1.	460	22500	20.4	21.3
2.	480	22500	21.3	
3.	495	22500	22.0	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.

Nitin Kumar Shukla
Assistant Professor

Nitin Kumar Shukla
Asst. Professor, CED
REC Ambedkar Nagar

Dr. Ayush Mittal
Assistant Professor
Dr. Ayush Mittal
Asst. Professor, CED
REC Ambedkar Nagar